



Characteristics and scope of application

- Filler metal for NiCu Alloys, excellent corrosion resistance in seawater environments
- Application in desalination plants and chemical process industry
- Recommended for dissimilar welds of NiCu alloys and mild steels

Standard designations

DIN EN ISO 18274	AWS A5.14	DIN Mat.-No.
S Ni 4060 (NiCu30Mn3Ti)	ERNiCu-7	2.4377

Typical chemical composition of filler metal

	C	Si	Mn	Cu	Ni	Ti
Mass %	0.02	0.3	3.3	29	Bal.	2.3

All weld metal properties (min. values at rt)

Heat treatment	Yield strength	Tensile strength	Elongation	Impact toughness	
	Rp0.2	R _m	A ₅	ISO-V	
as welded	300 MPa	450 MPa	30%	120 J	

Welding instructions

Polarity	Shielding gas acc. to DIN EN ISO 14175
DC / +	I1, I3, Z (ArHeHC-30/2/~0.1)
DC / -	I1, I3, R1 (max. 5% H ₂)

Low heat input and interpass temperature < 120°C. Stringer bead technique recommended.

Base materials
2.4360 – NiCu30Fe – Alloy 400
2.4375 – NiCu30Al – Alloy K 500

Packaging (tolerances acc. to DIN EN ISO 544)

Approvals on request

Diameter (mm)		kg
1.6 / 2.0 / 2.4 / 3.2	X 1000 mm	5 / 10
0.8 / 1.0 / 1.2	BS 300 spool	15
1.6 / 2.4 / 3.2	K 415 / K 435 spool	25